

# DURALUBE MY2HV

GREASE  
Technical Data Sheet

## LUBRICATING GREASE

### PRODUCT DESCRIPTION

**Duralube MY2HV** is a lubricating grease formulated to meet the extreme conditions encountered in off-highway construction equipment as well as heavy duty applications. This product is a lithium complex thickened grease blended with high viscosity base fluids for exceptional film strength and is fortified with molybdenum disulfide for additional load carrying capacity and anti-wear performance. In addition, Duralube MY2HV contains a unique blend of extreme pressure, anti-wear and rust and oxidation inhibitors as well as functional polymers for better adhesion in wet environments and better performance at higher temperatures. Because it is a lithium complex thickened grease, Duralube MY2HV has a high dropping point which also provides excellent protection in high temperature environments.

### TYPICAL PROPERTIES

NLGI Grade		2
Color		Gray
Texture		Tacky
Thickener Type		Lithium Complex
Penetration	ASTM D 217	
Worked 60 Strokes		265-295
Dropping Point	ASTM D 2265	500°F (260°C) min
4 Ball Wear Test, mm Scar Diameter	ASTM D 2266	0.75 max
4 Ball E.P. kg	ASTM D 2596	500
LWI	ASTM D 2596	45 min
Timken Load Carrying Test of Grease, lbs	ASTM D 2509	55
Rust Preventative Properties of Greases	ASTM D 1743	Pass
Copper Corrosion of Greases	ASTM D 4048	1b
Water Washout, 175°F (79°C), % loss	ASTM D 1264	5 max
Molybdenum Disulfide, Percentage		3.0 min
Base Fluid Type		Petroleum Mineral Oil
Base Oil Characteristics (listed without polymer)	ASTM D 445	
Viscosity @ 40°C, cSt		327-350
Viscosity @ 100°C, cSt		22-24.5
Viscosity @ 100°F, SUS		1,715-1,875
Viscosity @ 210°F, SUS		110-122
Viscosity index		80 min

### PRODUCT NUMBER

LXM2704000

### HEALTH AND SAFETY

For health and safety guidance, please refer to the Chemtool SDS (Safety Data Sheets).



801 W Rockton Road, Rockton, IL 61072 • Phone: 815-957-4140 • Fax: 815-624-0381 • [www.chemtool.com](http://www.chemtool.com)

This information is presented in good faith, but no warranty, express or implied, is given nor is freedom from any patent owned by Chemtool Incorporated or by others to be inferred. The final determination of the suitability of the products for the application contemplated by the user is the sole responsibility of the buyer. REV 03/01/16